

ABRASION RESISTANT PLATE

Hardox 600 is an abrasion resistant plate with a hardness of 600 HBW, intended for applications requiring an extremely high abrasion resistance.

Applications Liners, cutters, feeders, shredders, hammers, knives etc.

Chemical Composition (ladle analysis)	Plate thickness	C	Si	Mn	P	S	Cr	Ni	Mo	B	CEV	CET
	inch	max	max	max	max	max	max	max	max	max	typv.	typv.
	$\frac{5}{16}$ - $\frac{1\frac{3}{16}}$	0.45	0.7	1.00	0.015	0.010	1.2	2.5	0.8	0.004	0.73	0.55
	$(\frac{1\frac{3}{16}}{2})$ -2	0.47	0.7	1.00	0.015	0.010	1.2	2.5	0.8	0.004	0.84	0.59

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40}$$

The steel is grain refined.

Hardness HBW
570 - 640

Impact Properties
Typical value for $\frac{3}{4}$ inch plate thickness

Testing temperature °F	Impact energy Charpy-V, longitudinal Ft-lbs (J)
-40 (-40°C)	15 (20)

Testing Brinell hardness, HBW according to EN ISO 6506-1, on a milled surface 0.02-0.12 inch below plate surface per heat and 40 metric tons. Tests are made for every variation of $\frac{5}{8}$ inch in the thickness of plates from the same heat.

Delivery Conditions Q.

Dimensions Hardox 600 is supplied in plate thicknesses of $\frac{5}{16}$ -2 inch. More detailed information on dimensions is provided in our brochure 41-General product information Weldox, Hardox, ArmoX and Toolox-UK.

Tolerances Thickness tolerances according to SSAB Oxelösund thickness precision guarantee AccuRollTech™, Class B. - AccuRollTech™ Class B meets the requirements of ASTM A6 but offers a more narrow tolerance width. More detailed information is given in our brochure 41-General product information Weldox, Hardox, ArmoX and Toolox-UK.

Flatness tolerances according to SSAB Oxelösund internal requirements, Class N. The SSAB Oxelösund requirements for Class N meet the flatness requirements of ASTM A6 but will be at least twice as close.

Surface Properties	According to ASTM A6.
General Technical	According to our brochure 41-General product information Weldox, Hardox, ArmoX and Toolox-UK.
Heat Treatment and Fabrication	<p>Hardox 600 has obtained its mechanical properties by quenching and when necessary by means of subsequent tempering. The properties of the delivery condition can not be retained after exposed to service or preheating temperatures in excess of 480°F (250°C). Hardox 600 is not intended for further heat treatment.</p> <p>For information concerning welding and fabrication, see our brochures on www.hardox.com or consult our Technical Customer Service.</p> <p>Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on the product. Grinding, especially of primer coated plates, may produce dust with high particle concentration. Our Technical Customer Service Department will provide further information on request.</p>

159-US, Hardox is a registered trademark of SSAB Oxelösund AB, Sweden.
The UK English version of this document shall prevail in case of discrepancy.
Download the latest version of this document on internet: www.ssab.com

SSAB Oxelösund AB, 613 80 Oxelösund, Sweden, +46 155 25 40 00, www.ssab.com

www.hardox.com

